

Application No.: 10/814,324
Response to Interview with Examiner
Attorney Docket: WETCO-001B

BEST AVAILABLE COPY

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application

Listing of Claims:

Claims 14-26, 28, 30 and 32 have been cancelled.

1. (Previously Amended) A method for controlling silica or silicate scale formation in an aqueous heat transfer water system with silica contributed by source water, the methods of the present invention comprising the steps:

- a) removing hardness ions from said source water;
- b) controlling the conductivity of said aqueous system water such that said aqueous system water possesses a measurable conductivity of at least 1 μ mhos ;
- c) elevating and maintaining the pH of said aqueous system water such that said aqueous system water possesses a pH of approximately 9.0 or greater; and
- d) providing a metallic heat transfer surface and cyclically contacting said aqueous system water thereabout.

2. (Original) The method of Claim 1 wherein in step a), said hardness ions comprise ions of calcium and magnesium.

3. (Original) The method of Claim 1 wherein said aqueous system water contains soluble SiO_2 residual that is at least 125 mg/L.

4 (Original) The method of Claim 3 wherein said aqueous system water contains soluble SiO_2 in excess of 200 mg/L.

5. (Original) The methods of the present invention of Claim 3 wherein in step a), said hardness ions are removed in amounts equal to or less than approximately 20% of the SiO_2 present within said source water.

6. (Original) The methods of the present invention of Claim 3 wherein in step a), said hardness ions are removed in amounts equal to or less than approximately 5% of the SiO_2 present within said source water.

7. (Original) The method of Claim 1 wherein in step c), said pH is maintained at 9.6 or higher.

Application No.: 10/814,324
Response to Interview with Examiner
Attorney Docket: WETCO-001B

BEST AVAILABLE COPY

8. (Original) The method of Claim 1 wherein in step a), said hardness ions are removed via a method selected from the group consisting of ion exchange, selective ion removal with reverse osmosis, reverse osmosis, electro chemical removal, chemical precipitation, evaporation and distillation.

9. (Original) The method of Claim 1 wherein in step c), said pH is increased by adding an alkali agent.

10. (Original) The method of Claim 9 wherein said alkali agent comprises sodium hydroxide.

11. (Original) The method of Claim 1 wherein in step c), said pH is elevated by evaporating a portion of said aqueous system water.

12. (Original) The method of Claim 1 wherein in step c), said pH is elevated by distilling a portion of said aqueous system water.

13. (Previously Amended) The method of Claim 1 wherein in step c), said aqueous heat transfer water system comprises water utilized for cooling processes, water utilized for cooling tower systems, water utilized for evaporative cooling, water utilized for cooling lakes or ponds, water utilized for enclosed or secondary cooling and heating loops.

14-26 (Cancelled)

27. (Original) The method of Claim 1 wherein prior to step a), said methods of the present invention comprises the step:

a) analyzing said source water to determine the concentration of SiO_2 present therein.

28. (Cancelled)

29. (Original) The method of Claim 1 wherein in step b), said conductivity of said aqueous system water is controlled such that said aqueous system water possesses a conductivity of at least 500 μmhos .

30. (Cancelled)

31. (Original) The method of Claim 1, wherein said source water contains silica in an amount of 4000mg/L or less.

32. (Cancelled)